

Amendments to the Claims

This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

Claim 1 (Currently amended): Self-adhesive surface protection film comprising a layered laminate produced by coextrusion, said laminate comprising:

- (a) a carrier layer and
- (b) an adhesive layer comprising a mixture of a styrene block copolymer and ~~a~~ at least one polyolefin, said at least one polyolefin being ~~or a polyolefin mixture~~ selected from the group consisting of polyethylene, and polypropylene ~~and amorphous poly- α -olefins.~~

Claim 2 (Original): The surface protection film according to claim 1 wherein said adhesive layer comprises a styrene block copolymer selected from the group consisting of:

a styrene/isoprene/styrene (SIS) copolymer,

a styrene/ethylene/butylene/styrene (SEBS) copolymer,

a styrene/ethylene/propylene/styrene (SEPS) copolymer, and

a styrene/butadiene/styrene (SBS) copolymer, or

a mixture of one or more styrene block copolymers selected from
said group.

Claim 3 (Original): The surface protection film according
to claim 1 wherein said adhesive layer comprises a styrene block
copolymer selected from the group consisting of:

a styrene/isoprene/styrene (SIS) copolymer, and

a styrene/butadiene/styrene (SBS) copolymer, and

having a di-block content of less than 15% by weight.

Claim 4 (Original): The surface protection film according
to claim 3, wherein the di-block content is less than 1 % by
weight.

Claim 5 (Original): The surface protection film according to claim 1 wherein said film has an adhesive strength after storage at room temperature for 24 hours of between 0.15 N/cm and 3.5 N/cm.

Claims 6-7 (Canceled).

Claim 8 (Original): The surface protection film according to claim 1, wherein said carrier layer is made from a polyolefin.

Claim 9 (Original): The surface protection film according to claim 1, further comprising a bonding agent layer arranged between said carrier layer and said adhesive layer.

Claim 10 (Original): The surface protection film according to claim 1, wherein said carrier layer has a thickness of 20 to 80 μm and said adhesive layer has a thickness between 4 and 20 μm .

Claim 11 (Original): The surface protection film according to claim 1, wherein said layered laminate produced by coextrusion has a release layer on a side of said carrier layer facing away from said adhesive layer.

Claim 12 (Original): The surface protection film according to claim 11, wherein said release layer comprises a member selected from the group consisting of talcum, chalk, silicic acid, polyamide wax, and mixtures thereof.

Claim 13 (Original): The surface protection film according to claim 11, wherein said release layer has a micro-embossed surface produced by an embossing roller.

Claim 14 (Withdrawn): The surface protection film according to claim 1 wherein said adhesive layer comprises a mixture of styrene/isoprene/styrene (SIS) copolymer and polyethylene.

Claim 15 (Withdrawn): The surface protection film according to claim 1 wherein said adhesive layer comprises a mixture of styrene/ethylene/butylene/styrene (SEBS) copolymer and amorphous poly- α -olefins.